

①



Europäisches Patentamt
European Patent Office
Office européen des brevets

⑪ Veröffentlichungsnummer:

0 123 949
A1

⑫

EUROPÄISCHE PATENTANMELDUNG

⑰ Anmeldenummer: 84103668.4

⑤① Int. Cl.³: **A 61 F 7/10, F 25 D 3/00**

⑱ Anmeldetag: 03.04.84

③① Priorität: 04.04.83 JP 48981/83 U

⑦① Anmelder: **NIPPON OIL CO. LTD.**, 3-12, 1-chome Nishi Shimbashi, Minato-ku Tokyo (JP)

④③ Veröffentlichungstag der Anmeldung: 07.11.84
Patentblatt 84/45


⑦② Erfinder: **Nambu, Masao**, 447-17, Honmoku Motomachi, Naka-ku Yokohama-shi Kanagawa-ken (JP)
Erfinder: **Kinoshita, Tatsuo**, 160-3, Takada, Chigasaki-shi Kanagawa-ken (JP)

⑥④ Benannte Vertragsstaaten: CH DE FR GB LI

⑦④ Vertreter: **Schübel-Hopf, Ursula et al, Strehl, Schübel-Hopf, Schulz Patentanwälte**
Widenmayerstrasse 17, D-8000 München 22 (DE)

⑤④ Verwendung eines verformbaren Beutels als Kälteträger.

⑤⑦ The bag (10) comprises small pieces (1) of a gel packed in a flexible envelope (2). The gel is prepared by casting into a mold an aqueous solution or suspension containing a polyvinyl alcohol and a water-soluble organic compound, and cooling the cast aqueous solution or suspension to -10 °C or lower and then partially dehydrating, without thawing, the thus obtained cooled mass in vacuum. The bag of the invention can be applied on different objects or portions having various configurations.



EP 0 123 949 A1

FIG.1




FIG.2




FIG.3




Fig. 4






Fig. 5










Fig. 11




Fig. 12





Fig. 10



TITLE OF THE INVENTION:

Deformable Bag for Use as Cooling Medium

BACKGROUND OF THE INVENTION:Field of the Invention;

5 The present invention relates to a deformable
bag for use as a cooling medium, and more particularly
it relates to a cooling bag which can be deformed
to fit to the contour of any portion of human or animal
body so as to cover intimately the portion to be cooled
10 thereby.

Prior Art;

 A variety of gel compositions have hitherto
been proposed to be used as cooling media and some
of them are applied for practical uses. Such a gel is
15 referred to as a cooling gel, chilling gel, coldness-
keeping means, coolant composition or ice pillow
without the need of ice. However, these known coolant
gels are extremely inconvenient in that they cannot
be deformed into any desired form other than the
20 designed forms, thus making it difficult to apply them
as universal cooling media for cooling general objects,
such as different portions of human body having various
configurations, although they can be effectively used for
cooling the target area of human body or other objects
25 having the configuration, in conformity of which the
known gels are preformed.

OBJECTS AND SUMMARY OF THE INVENTION:

5 A primary object of this invention is to provide a deformable bag for use as a cooling medium which can be applied universally on different objects or portions having various configurations.

Another object of this invention is to provide a deformable bag for use as a cooling medium and having comfortable touch to human body.

10 A further object of this invention is to provide a deformable bag for use as a cooling medium, the bag comprising a plurality of small pieces of a gel having a high water content and no tendency of sticking with one another, thus being moved smoothly in the bag when the bag is deformed.

15 The deformable bag for use as a cooling medium, according to the present invention, comprises a plurality of small pieces of a gel having a high water content and packed in a flexible envelope, said gel being prepared by the steps of preparing an aqueous solution or suspension
20 of a mixture of a water-soluble organic compound and a polyvinyl alcohol having a degree of hydrolysis of not less than 95 mol% and an average polymerization degree of not less than 1,100, the concentration of said organic compound in said mixture being adjusted to be in the
25 range of from 5 to 40 wt% and the concentration of said polyvinyl alcohol in said mixture being more than 8 wt% and

not more than 25 wt%, casting said aqueous solution or suspension into a mold having desired shape and dimensions, cooling the cast aqueous solution or suspension to a temperature of not higher than - (minus) 10°C to solidify the same to form a molded mass of solidified gel, and then partially dehydrating, without thawing, the molded mass of solidified gel in vacuum until the percentage dehydration rate (the weight reduction rate of the solidified gel) reaches not less than 3 wt%.

10 BRIEF DESCRIPTION OF THE DRAWING:

The single Figure 1 in the appended drawing is a schematic illustration showing one embodiment of the deformable bag according to this invention.

DESCRIPTION OF THE INVENTION:

15 The present invention will now be described in detail hereinafter.

The polyvinyl alcohol used in the present invention should have a degree of hydrolysis of not less than 95 mol%, preferably not less than 97 mol%. If a polyvinyl alcohol having a degree of hydrolysis of 80 to 88 mol%, particularly less than 85 mol%, is used, the resultant gel is weak and crumble. A gel having rubber-like elasticity cannot be formed from a polyvinyl alcohol having such a low degree of hydrolysis. It is also essential that the polymerization degree of the used polyvinyl alcohol be not less than 1,100. If the

polymerization degree of the used polyvinyl alcohol is less than the defined range, the mechanical strength of the resultant gel is lowered. It is preferred that a polyvinyl alcohol having a polymerization degree of from 1,100 to about 3,300 is used. Commercially available polyvinyl alcohol products having a polymerization degree ranging within 1,100 to 2,600 may be used.

In the first step for the preparation of the bag according to the invention, an aqueous solution or suspension containing the aforementioned polyvinyl alcohol and a water-soluble organic compound is prepared. The concentration of polyvinyl alcohol in the aqueous solution or suspension should be more than 8 wt% and not more than 25 wt%, preferably in the range of from 9 to 15 wt%. If the concentration of polyvinyl alcohol is more than 25 wt%, the resultant gel becomes too hard and gives somewhat uncomfortable touch when used as a cooling medium. On the contrary, if the concentration of polyvinyl alcohol is less than 8 wt%, the resultant gel is too weak to crumble away during the use as a cooling medium.

According to one important aspect of the present invention, the aqueous solution of aforementioned polyvinyl alcohol is added with a water-soluble organic compound prior to gelation. The water-soluble organic compound added to the solution of polyvinyl alcohol is selected from those which are used as antifreezing agents, and

acts as the freezing point depressing agent. Examples of water-soluble organic compounds, which may be used in preparation of the gel contained in the bag of the invention, are water-soluble monohydric alcohol and derivatives thereof, such as methyl alcohol, ethyl alcohol and isopropyl alcohol; water-soluble polyhydric alcohols, such as ethylene glycol, propylene glycol, 1,3-propylene glycol, glycerin, and 2-methyl-2,4-pentanediol; and other water-soluble organic compounds, such as acetone, dimethylsulfoxide, methylsulfonic acid, ethylsulfonic acid, dimethylamine, methylamine and formic acid. Further examples of suitable compounds are monosaccharides, such as erythritol, arabinose, xylose, xylitol, glucose, glucitol (sorbitol or sorbite), gluconic acid, glucuronic acid, glucaric acid, galacturonic acid, fructose and glucosamine; disaccharides, such as sucrose, cellobiose and lactose; trisaccharides, such as raffinose; and water-soluble polysaccharides, such as agarose, amylose, sodium alginate, glycogen, chondroitin, chondroitin sulfuric acid, dextran, pectic acid, propylene glycol alginate, tragacanth gum, pullulan, and chondroitin sodium sulfate. Ethylene glycol, propylene glycol, glycerin and D-sorbitol are particularly preferred, since they are odorless and less volatile and have the advantage that the freezing point of the admixture can be depressed by adding a relatively small quantity thereof with

appreciable contribution to improvement in mechanical strength of the resultant gel.

The concentration of the aforementioned water-soluble organic compound in the aqueous solution or suspension should be within the range of from 5 to 40 wt%, preferably from 10 to 35 wt%. If the concentration thereof is lower than 5 wt%, it becomes difficult to lower the freezing point of the solution below -10°C . If the concentration thereof is higher than 40 wt%, the freezing point of the solution is excessively lowered or the freezing point is rather raised. Anyway, excess addition of the water-soluble organic compound increases economical expense with no technical merit. By the addition of the aforementioned water-soluble organic compound, the freezing point of the gel is depressed below -20°C , and thus the gel may be cooled in an ice-box (generally maintained at a temperature of from -10°C to -20°C) of a general household refrigerator without being frozen to retain the elasticity and soft touch resembling the living tissues.

In preparation of the aforementioned aqueous solution or suspension containing both of the polyvinyl alcohol and the water-soluble organic compound acting as the antifreezing agent; the polyvinyl alcohol and one or more of the water-soluble organic compounds are added to water simultaneously to be dissolved or suspended in water; the polyvinyl alcohol is initially dissolved in water and then

the solution is added to the water-soluble organic compound or an aqueous solution thereof; or the water-soluble organic compound or an aqueous solution thereof is mixed with an aqueous solution of the polyvinyl alcohol or mixed with the polyvinyl alcohol of powder form. Irrespective of the method adopted for the preparation of the solution or suspension, the concentration of polyvinyl alcohol is adjusted to be within the range of more than 8 wt% and not more than 25 wt% and the concentration of water-soluble organic compound is adjusted to be within the range of from 5 to 40 wt%.

In the present invention, the aqueous solution or suspension containing the aforementioned polyvinyl alcohol and the aforementioned water-soluble organic compound is cast into a mold having desired shape and dimensions followed by cooling to obtain a molded mass of solidified gel.

At the cooling step, the aqueous solution or suspension is cooled to a temperature of lower than -10°C , using a coolant selected from cryogens, such as sodium chloride-ice (23:77, -21°C) and calcium chloride-ice (30:70, -55°C), dry ice-methyl alcohol (-72°C) and liquefied nitrogen (-196°C). Although the aqueous solution or suspension may be cooled to -269°C by the use of liquefied helium, the use of liquefied helium is not recommendable from the economical viewpoint.

without any merit for improving the quality of the resultant gel. In practical operation, a freon refrigerator is used to cool the solution or suspension to a temperature of from -20°C to -80°C . The cast
5 solution or suspension may be, of course, cooled in an ice-box (maintained at -10°C to -20°C) of a household refrigerator. The cooled mass is then subjected to dehydration in vacuum to form a solidified gel. The cast mass should be cooled sufficiently, since
10 insufficient cooling results in inferior mechanical strength of the resultant gel.

Accordingly, in the present invention, the aqueous solution or suspension containing the polyvinyl alcohol and one or more water-soluble organic compounds
15 should be cooled to below -10°C , preferably below -15°C .

According to another important aspect of the invention, the cooled mass is then dehydrated in vacuum without thawing. The mechanical strength of the gel is improved as the percentage dehydration rate (i.e. the
20 weight reduction rate of the cooled and solidified gel) is increased. However, in view of the application as the cooling medium, it is not necessary to increase the percentage dehydration rate so high as to obtain a gel having extremely high mechanical strength. It is
25 preferred, in consideration of the softness and elasticity of the resultant gel, that the percentage of the

dehydration rate be controlled to not less than 3 wt%, preferably within the range of from 3 wt% to 35 wt%. The dehydration in vacuum means the dehydration under a reduced pressure. The pressure is not particularly a critical parameter, and dehydration may be effected at a pressure of not higher than 1 mmHg, preferably not higher than 0.1 mmHg and more preferably not higher than 0.08 mmHg.

In the present invention, small pieces of solidified gel are formed from the thus obtained gel having a high water content by casting the aqueous solution or suspension containing the polyvinyl alcohol and one or more water-soluble organic compounds into a plurality of molds for molding small pieces of molded mass having desired shape and dimensions. Otherwise, a molded mass having larger dimensions may be cut to a plurality of small pieces having desired shape and dimensions. The shape of small pieces of high water content gel is not limited and may be cubic, rectangular parallelepiped cylindrical or spherical. The dimensions of the gel pieces are not critical, and it suffices that each piece is small enough to move smoothly in the envelope to deform the bag. It is generally preferable that each piece has the dimensions, i.e. the length of each side or diameter, ranging within 2 mm to 5 cm.

- 10 -

A plurality of small pieces of the gel having high water content is put into a flexible envelope and the opening of the envelope is closed. Preferable materials for the flexible envelope include plastic
5 films, such as polyethylene, polypropylene and polyvinylchloride films. These films are preferred because they provide comfortable touch to human body and durable sealing properties.

Small pieces of high water content gel are
10 packed in the envelope such that about 50 to 90 vol% of the space enclosed by the envelope is occupied by the packed gel pieces. The volume percentage occupied by the packed gel pieces is not a critical parameter, provided that the packed gel pieces are movable within
15 the envelope to realize deformation of the bag. The shape and dimensions of the bag are not limited. For example, a rectangular parallelepiped bag having the dimensions of 20 x 15 x 4 cm may be prepared and used generally for cooling any desired portion of human
20 body. The doubled or tripled envelopes may be used to prevent the enclosed gel pieces from getting out of the envelope even when one of the envelope is broken.

To close the opening of the envelope, fastener means including a groove extending along one side
25 edge of the opening and a projection extending along the opposing side edge of the opening may be provided

to engage with each other after the gel pieces are packed in the envelope. When an envelope made of a plastic film is used, the opening of the envelope may be closed by hot melting. Otherwise, the opening of the envelope may be tied up by means of a string or cord, or the end of the opening may be folded and then sewn together. The opposing faces of the edge of the envelope may be joined together using an adhesive. The gel pieces of high water content are enclosed in the envelope by any means.

The envelope may be provided with a cord or strip for tying each other after the bag is applied to a desired portion to be cooled. The cord or strip may be provided with a "velcro" fastener (Trade Mark), which is a material having a surface with projecting fibers for releasably engaging projecting fibers on another surface. Alternatively, the bag may be fixed by winding a bandage around the bag.

The bag according to this invention comprises a plurality of small gel pieces movably enclosed in an envelope, and can be deformed freely after it is cooled so that it covers intimately any curved portion, such as throat, leg, arm, head, auricular region, inguen chin, eyelid, face, axillary region or breast, to cool effectively the portion on which it is placed.

EXAMPLE OF THE INVENTION:

A preferred embodiment of this invention will now be described with reference to the appended drawing.

Example:

5 1 kg of a 10 wt% aqueous solution of a
polyvinyl alcohol having a degree of hydrolysis of
99.5 mol%, an average polymerization degree of 2,600
and a viscosity at 20°C of a 4% aqueous solution of 67
centipoises was mixed with 500g of propylene glycol.
10 The mixture was cast into a stainless steel mold, and
cooled at -42°C for 14 hours. The cooled mass was then
subjected to dehydration in vacuum without thawing
to remove 200g of water, followed by allowing to stand
at room temperature, to obtain a rectangular
15 parallelepiped gel having the dimensions of 24 cm x 20 cm
x 2.7 cm.

 The gel mass was cut into pieces of
parallelepiped having average dimensions of 1 cm x
1.2 cm x 0.3 cm. About 3500 small pieces 1 were
20 prepared. The small pieces 1 (about 3000 pieces) of the
gel were packed in a polyethylene envelope 2 (20 cm
x 15 cm x 4 cm) so that about 75 vol% of the space
enclosed by the envelope 2 was occupied by the packed
gel pieces. The envelope 2 was provided with a groove
25 3 and a projection 4 extending along the edges of the
opening of the envelope 2 to form fastener means 5.

After packing the gel pieces 1, the fastener means 5 was closed to sealingly enclose the gel pieces to prepare a bag 10 adapted for use as a cooling medium.

5 The thus prepared cooling bag 10, according to the present invention, was allowed to stand in an ice-box (maintained at -22°C) of a refrigerator for 2 days to reveal that the small gel pieces 1 did not become rigid and retained the softness and elasticity.

10 The cooled bag 10 was placed on the throat of a patient to reveal that the bag 10 was deformed in conformity with the contour of the throat portion to cover intimately and to cool effectively the applied portion. The final composition of the gel was composed of 7.5 wt% of polyvinyl alcohol, 38 wt% of propylene glycol and 54 wt% of water.
15

WHAT IS CLAIMED IS:

1. A deformable bag for use as a cooling medium comprising a plurality of small pieces of a gel having a high water content and packed in a flexible envelope,
5 said gel being prepared by the steps of preparing an aqueous solution or suspension of a mixture of a water-soluble organic compound and a polyvinyl alcohol having a degree of hydrolysis of not less than 95 mol% and an average polymerization degree of not less than
10 1,100, the concentration of said organic compound in said mixture being adjusted to be in the range of from 5 to 40 wt% and the concentration of said polyvinyl alcohol in said mixture being more than 8 wt% and not more than 25 wt%, casting said aqueous solution
15 or suspension into a mold having desired shape and dimensions, cooling the cast aqueous solution or suspension to a temperature of not higher than - (minus) 10°C to solidify the same to form a molded mass of solidified gel, and then partially dehydrating,
20 without thawing, the molded mass of solidified gel in vacuum until the percental dehydration rate (the weight reduction rate of the solidified gel) reaches not less than 3 wt%.
2. The deformable bag as claimed in claim 1,
25 wherein said mold having desired shape and dimensions includes a plurality of mold sections for molding

small pieces of gel of finished shape and dimensions.

3. The deformable bag as claimed in claim 1, wherein said mold having desired shape and dimensions is a mold for molding a gel mass of larger dimensions, and
5 said gel mass of larger dimensions is cut to form a plurality of said small pieces of said gel.


4. The deformable bag as claimed in claim 1, wherein the opening of said envelope is provided with fastener means including a groove extending along
10 one edge of the envelope and a projection extending along the opposing edge of the envelope to be firmly received in said groove.

5. The deformable bag as claimed in claim 1, wherein said bag is provided with a cord or strip for
15 fixing the bag at a desired position.

6. The deformable bag as claimed in claim 5, wherein said cord or strip is provided with a material having a surface with projecting fibers for releasably engaging projecting fibers on another surface.

-1/1-

FIG. 1





European Patent
Office

EUROPEAN SEARCH REPORT

0123949
Application number

EP 84 10 3668

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 7)
Y	FR-A-1 365 666 (LOINTIER et al.) * Page 1, right-hand column, lines 4-21; figure *	1	A 61 F 7/10 F 25 D 3/00
Y	FR-A-2 202 265 (GUILLON et al.) * Claim 1 *	1	
A	GB-A-1 404 171 (UNION CARBIDE CORP.)		
A	US-A-4 324 111 (EDWARDS)		
A	US-A-3 885 403 (SPENCER)		
A	US-A-3 545 230 (MORSE)		
			TECHNICAL FIELDS SEARCHED (Int. Cl. 7)
			A 61 F 7/00 F 25 D 3/00
The present search report has been drawn up for all claims			
Place of search BERLIN		Date of completion of the search 28-06-1968	Examiner KANAL P K
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP2004/011332

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 A61F7/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 A61F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)
EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	FR 1 018 835 A (GOODRICH CO B F) 13 January 1953 (1953-01-13) page 1, right-hand column, paragraph 4 - page 2, left-hand column, paragraph 3; figures 1,2	1
A	DE 34 44 066 A (KNEIPP WERKE KNEIPP MITTEL ZEN) 5 June 1986 (1986-06-05) column 11, line 1 - line 10; figures 1,2	1
A	US 5 069 208 A (NOPPEL RENE ET AL) 3 December 1991 (1991-12-03) column 3, line 57 - column 4, line 30; figure 3	1

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

*** Special categories of cited documents:**

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

22 February 2005

Date of mailing of the international search report

28/02/2005

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Mayer-Martenson, E

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP2004/011332

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
FR 1018835	A	13-01-1953	NONE	
DE 3444066	A	05-06-1986	DE 3444066 A1 AT 53289 T WO 8603400 A1 EP 0247037 A1 JP 62501478 T	05-06-1986 15-06-1990 19-06-1986 02-12-1987 18-06-1987
US 5069208	A	03-12-1991	AT 66360 T AU 7039687 A WO 8706825 A1 DE 3772339 D1 EP 0270553 A1	15-09-1991 01-12-1987 19-11-1987 26-09-1991 15-06-1988